


SPECIFICATION FOR APPROVAL

1. Material

Production:	Iron Powder Cores
KDM.P/N:	KT130-26
A_L :	$81(\text{nH}/\text{N}^2) \pm 10\%$
Material:	-26
Coating Color:	Yellow/White
Coating material:	epoxy
Coating Breakdown Voltage:	600Vrms.0.5mA. 2sec




2. Physical Characteristics

After Coating			l_e (cm)	A_e (cm ²)	V (cm ³)	W (cm ²)	Weight	Box Quantity (Pieces)
OD mm	ID mm	Ht mm						
33.00 ± 0.50	19.80 ± 0.50	11.10 ± 0.65	8.280	0.698	5.780	3.077	41.70g	336

3. Electrical Parameters(Typical) Temperature(25°C ± 2°C)

Test Item	Test Condition	Value(Typical)
Inductance	ϕ 0.29mm/10Ts, 10kHz/1V, $I_{DC}=0A$	8.10 μ H ± 10%
DC-Bias	ϕ 0.5mm/55Ts, 10kHz/1V, L(6.0A)/L(0A) × 100%($H_{DC}=50Oe$)	46%(Min.)
Core Loss	100kHz/140Gs	96mW/cm ³ (Max.)
Q	ϕ 0.29mm/10Ts, 200kHz/1V, $I_{DC}=0A$	6.0(Min.)
Remarks		

DC-Bias Curves(Typical)



Core Loss Curves(Typical)

